



**M. J. Bradley & Associates**

1000 Elm Street  
Second Floor  
Manchester, NH 03101

Tel: 603-647-5746  
Fax: 603-647-0929  
[www.mjbradley.com](http://www.mjbradley.com)

June 17, 2013

Ms. Elizabeth Kudarauskas  
US EPA Region I  
5 Post Office Square, Suite 100  
Mail Code: OES-04-2  
Boston, MA 02109-3912

Mr. William Osbahr  
US EPA Region I  
Mail Code EIA  
11 Technology Drive  
North Chelmsford, MA 01863-2431

**Re: Global Partners LP Asphalt Vapor Pressure Test Results as Required Under Section 114 Testing Order**

Global Partners LP (Global) submits the attached laboratory analysis for vapor pressure of liquid asphalt from the South Portland Terminal. This submittal fulfills Testing Order 7.b of the Section 114 letter issued to Eric Slifka, President and CEO of Global Partners LP dated November 2, 2011.

The vapor pressure results for different temperatures are provided in the attached Test & Evaluation Report provided by PRI Asphalt Technologies, Inc. The asphalt liquid sample was collected on July 29, 2012 at 10:15 am from Global's South Portland Terminal Tank 9. The asphalt temperature on the day the sample was collected was 303 F. The asphalt contained in Tank 9 was delivered to the South Portland Terminal on July 28-29, 2012 by Sargeant Ltd and came from the ASES Refinery in Tarragona, Spain.

The delay between the asphalt sample collection and the analysis was due to the trouble finding a laboratory capable of performing a vapor pressure analysis on asphalt (very rare request). The PRI Asphalt Technologies laboratory in Tampa, FL was the only lab Global could find who would do any vapor pressure testing on asphalt and they could only do ASTM D2879. As such, Global was unable to fulfill EPA's request for an additional vapor pressure analysis using ASTM D323-82 or 94. Global diligently made inquiries with several petroleum labs, local collages, environmental labs and with Bill Osbahr of EPA, and none had any guidance for doing ASTM D323-82 or 94 on an asphalt sample.

If you have any questions, please do not hesitate to call me, at (603) 647-5746 ext 102.

Sincerely,

A handwritten signature in black ink, appearing to be 'SVP', with a long horizontal line extending to the right.

Stephen Piper, P.E.  
Senior Project Manager

Cc: Ron Kenny, Global Area Operations Manager  
Bruce Yates, Global South Portland Terminal Manager  
Tom Keefe, Global Director of EHS Operations

Attachment: Test & Evaluation Report



# ASPHALT TECHNOLOGIES, INC.



## TEST & EVALUATION REPORT

June 6, 2013

Report For: Global Companies, LLC  
P.O. Box 2678  
South Portland, ME 04116-2678

Attn: Bruce A. Yates, Jr.

Email: [byates@globalp.com](mailto:byates@globalp.com)

### Sample Data/Information:

Sample ID: PG 64-22, Tank 9, Vessel: Asphalt Star	Project #: GLBL-01-02-01
Date Received: 5/6/13	Supplier: Global Companies

OBJECTIVE: Test and evaluate sample in accordance with ASTM D 2879/EPA for Vapor Pressure.

### DATA/RESULTS:

Property	Test Method	Results
Vapor Pressure, mm of Hg (atm)	ASTM D 2879 / EPA	200°F 3.5 (0.005)
		250°F 23.8 (0.031)
		300°F 44.9 (0.059)
		350°F 77.2 (0.101)

DISCUSSION: Results are listed in the table above.

Tested by: Stanley R. Prince  
Stanley Prince, Ph.D., Lead Scientist

Date: June 6, 2013

Reviewed by: Kenneth F. Grzybowski  
Kenneth F. Grzybowski, President

Date: June 6, 2013

GLBL-01-02-01

Accreditations: AASHTO/AAP; an ISO/IEC 17025 Lab

The test results, opinions, or interpretations are based on the material supplied by the client. This report is for the exclusive use of stated client. No reproduction or facsimile in any form can be made without the client's permission. PRI Asphalt Technologies, Inc. assumes no responsibility, nor makes a performance or warranty statement for this material or products and processes containing this material in connection with this report.

PRI Asphalt Technologies, Inc. · 6408 Badger Dr. · Tampa, FL 33610 · Tel: 813-621-5777 · Fax: 813-621-5840 · e-mail: [kgrzybowski@priasphalt.com](mailto:kgrzybowski@priasphalt.com) · Website: <http://www.priasphalt.com>